

Standard kulørt passepartout karton

Producer: Moorman, Holland

Core (woodpulp):

Made from a mixture of groundwoodpulp, bleached chemical pulp and recycled pulp. It is buffered with 4% (Calcium carbonate) CaCo_3 to make it pH neutral.
pH value abt. 8.3 ± 0.5

Lining paper (back):

The back is the side that comes into contact with the artwork. We only use very high quality paper for the back of all matboards. Paper that is acidfree, pH value abt. 7.8 ± 0.5 , buffered with minimum 3% Calcium carbonate (CaCo_3), which ensures that every Moorman matboard is of a top quality

Face paper(front):

The surface paper needs to meet high requirements. We therefore obtain the surface papers from highly specialized papermills. The surface can be paper, linen or suede.

TECHNICAL SHEET



J&M Handel Aps • Foldagervej 3-5 • DK 4623 Lille Skensved
Tlf.: 7015 3620 • www.jmhandel.dk • info@jmhandel.dk