

SYREFRI BAGPAP

GENERAL

Backing Board no 1 is designed for applications where some protection to acidity is required. The board is laminated with 400 gsm, wood-free, acid-free paper. The back side is a fully coated FBB board.

APPLICATIONS

Backing Board no 1 is well suited for framing of photos, art and graphical sheets etc.

Substance gsm	Thickness μm	Bending stiffness Resonance mNm	
		MD	CD
1500	2500	∅	∅

∅ Values can not be measured

Property	Target	Tolerance
Substance, gsm ISO 536	As specified	+/- 10%
Thickness, μm ISO 534	As specified	+/- 10%
Scott Bond, J/m ² TAPPI 569	150	Min 100
RH	50-55%	

400 GR. SYREFRI TOPLINER

General technical spec. for Natural white, acid-free liner on Backing board

Specifications

- pH 7,5-9,5
- Buffered min 2,0%
- Reducible sulphur: less than 0,5 ppm
- Neutral sized
- Lignin free
- Lightfast
- Free of optical brightening agents
- Contains no plasticisers
- Passes P.A.T test
- Complies to DIN 6738:1992 life span 12-80
- Complies to ANZI/NIZO Z39.48-1992
- Complies to ISO CD 9706:1994

Acid-free surface on Backing board fulfills above requirement

TECHNICAL SHEET

